

7120 SFR M12 Superfast

HS Ultra Rapid Surfacers

silco[®]

Ultra fast drying surfacer for perfect
refinish results within minutes.

- / Exceptionally fast drying times
- / Sanding after 15 minutes at 20°C
- / Easy sanding without paper clogging
- / Excellent adhesion on various substrates
- / Very easy application with short flash-off time
- / Excellent adhesion of basecoats and topcoats



7120 SFR M12 Superfast

HS Ultra Rapid Surfacer

Mixing ratio 5:1

Hardener	Standard 7125
<hr/>	
Drying time*	
20°C	15 min
60°C	5 min
IR	5 min
Flash-off untill matt	1–2 min
Potlife	35 min
Thinner	10–20 % 7030 Fast / 7050 Standard / 7070 Slow

*Indicative times subject to thinner type/
application/wet film thickness/environment ...

How to use?

Use of slow thinner is recommended in case of higher temperatures in combination with larger surfaces. Light half coat followed by full closed coat with 1 minute flash-off can be used for priming. This way you achieve up to 80 microns of dry film with 15 minutes sanding time. Two normal full coats (with 2-3 minutes flash-off) and up to 120 microns will result in 20 minute sanding time.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

Top-quality acrylic primer-filler with exceptionally fast drying time suitable for fast repair process of small and larger surfaces. The filler is air dry in 15 minutes at 20°C. Possible to apply to bare metal. The surface is smooth, sanding after 15 minutes from application is easy without paper clogging.

Packaging

Primer / 7120 SFR M12 Superfast HS Ultra Rapid Surfacer

Prod. Nr.	Content	Color
7120-A-3,5	3.5 L	White
7120-B-3,5	3.5 L	Dark grey
7120-C-1	1L	Grey
7120-C-3,5	3.5 L	Grey

Hardener / 7125 HS Hardener HS Acrylic Hardener – mixing ratio 5:1

Prod. Nr.	Content	Description
7125-0,2 / 7125-0,7	200 ml / 700 ml	Standard