

Description

1K black matt paint based on quality nitrocellulose resin.





Features & Benefits

- high covering power
- quick drying
- durability

Substrate preparation

Covered surface must be clean, sanded, dry and degreased.

Application data

	Mixing ratio	Thinner, 7050 50 – 100 % vol.
Shake and mix well before use!		
	Spray gun set /air inlet	Gravity feed 1,3 - 1,5 mm 1,8 – 2,0 bar Suction feed Verify manufacturer's info
	Application	Number of coats 1 – 2 coat Flash off 5 – 10 min Total dry film build 30 – 50 microns
	Drying	Dust dry (20 °C/68 °F) 15 – 20 min Touch dry (20 °C/68 °F) 120 – 180 min Total hardness (20 °C/68 °F) 24 h Pot life at 20 °C/68 °F -

Prod. Nr.	Description	Volume	Packaging Box
7170-0,75	Black	0,75 L	6

VOC

VOC 2004/42/IIB(a)(840) <840

Shelf life

Min. 24 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.