

9130 X13 Spectrum

UHS 420 Rapid Clear Coat

Fast drying clear coat for complete resprays or spot repair.

silco[®]

- / Very fast drying
 - 10 minutes at 60°C
 - 2.5 hours at 20°C
- / Immediate polishing after cooling down
- / Superior gloss retention & UV protection
- / Very easy application & leveling

www.silco.si/en



9130 X13 Spectrum

UHS 420 Rapid Clear Coat

Mixing ratio 2:1

Hardener	Extra Fast 9122	Fast 9123	Standard 9125	Slow 9127
Drying time*				
20°C/68°F	2–3 h	3 h	3–4 h	5–6 h
60°C/140°F	10 min	10 min	15 min	15–20 min
IR	7 min	10 min	10–15 min	15 min
Flash-off 20°C/68°F	5–10 min			
Potlife 20°C/68°F	>60 min			
Thinner	5–15 % (7030 Fast, 7050 Standard, 7070 Slow)			

*Indicative times subject to hardener and thinner type/application/environment...

How to use?

Fast hardeners are recommended only for vertical surfaces and low temperatures. Light half coat followed by full closed coat without flash off can be used for spot and quick repairs. For all other repairs, use two full coats application method, with flash off between coats (5 min). Flash off time and drying time depends on the combination of the hardeners and thinners used.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

Clear coat of highest quality with perfect drying profile and deep gloss for the most demanding refinish projects.

Application of X13 Clear Coat is very easy and the overflow/leveling of the product is perfect. X13 Clear is characterized by superior gloss retention and UV resistance. Polishing is possible immediately after cooling down.

Packaging

9130 X13 Spectrum
UHS 420 Rapid Clear Coat

Prod. Nr.	Content
9130-1	1 L
9130-5	5 L

Hardener / 9122 - 9127 HS Hardener
HS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9122-0,5 / 9122-2,5	500 ml / 2.5 L	Extra Fast
9123-0,5 / 9123-2,5	500 ml / 2.5 L	Fast
9125-0,33 / 9125-0,5 / 9125-1 / 9125-2,5	330 ml / 500 ml / 1 L / 2.5 L	Standard
9127-0,5 / 9127-1	500 ml / 1 L	Slow